

Management of Iron Ore Fines For Yield Improvement: A Case Study of Dalli-Rajhara

S. Manoj Kumar
Research Scholar,
School of Humanities
Lovely Professional University,
Phagwara, (Punjab).

and

Dr. Anand Kumar
Assistant Professor
School of Humanities,
Lovely Professional University,
Phagwara, (Punjab).

ABSTRACT

“A journey of a thousand miles begins with a single step” - **Confucius**

Beneficiate ore, improve yield, conserve mineral & develop sustainably.

Quality of fines has to meet the technological requirement of customers in terms of size, desired lower alumina and silica content. Conventional iron ore processing generates slimes to the tune of 10 to 15 % of run-off-mine (ROM). Low grade fines and slime occupy huge space and cause environmental and ecological problems.

Adoption of a combination of techniques for mining, beneficiation, sintering and pelletisation of ore has resulted in increased use of the fines in iron making. Low-grade ores, with iron content lower than 58% are now used, resulting in increase in mine life and reduction of waste, thereby reducing the need for additional land to dump the waste.

Techniques such as Dredge Mining from slime pond, alternate use of BHQ (Banded Hematite Quartzite) in blast furnace and recycling of waste materials have proven result in reduction in consumption of iron ore per ton of hot metal.

The scope of this paper confines to the ore fines of Dalli-Rajhara. The said deposits show characteristics of low to moderate grade ore which comprises Hematite and Goethite as ore minerals and Quartz, Pseudo Ore and Ferruginous Clay as gangue minerals. Ore minerals distribution is around 28% as a whole and gangue minerals distribution is around 72% area as whole.

Main ore mineral is Hematite with 20% area out of which around 6% grains are in free-state and remaining 14% grains are in un-liberated state. Around 7% un-liberated grains could be liberated at 20 micron size. Remaining grains are in less than 15 micron size.

Goethite covers around 10% area as a whole. All Goethite grains are in less than 30 micron size, out of which around 2% grains are in free-state and remaining 8% grains are not liberated. All un-liberated grains are in less than 20 micron size.

About 9.47 Mt of low grade fines (in course of manual mining in the past) is available and around 14.5 Mt of slimes have accumulated in the tailing dam. Exploratory works

1. AGM, CET, Bhilai Sub Centre, 2. Sr.Mgr.(Mines-Project), BSP

have proved more reserves in the wake of lowering of mining cut-off grade from 55% to 45%. The resource base adds to sustenance.

Amenability to beneficiation has been established through lab scale and pilot scale tests. Since the products of slime beneficiation will be of very fine nature, Pelletisation shall be the next logical step. Adverse environmental impact due to accumulated slime, dumped low grade fines shall be mitigated.

Charging of pellets in blast furnaces will improve the performance of the furnaces, which will be reflected in lower coke rate, higher productivity and improved hot metal quality.

“A journey of a thousand miles begins with a single step”- **Confucius**
Beneficiate ore, improve yield, conserve mineral & develop sustainably.

FOREWORD

The exploitation of low quality iron ore and fines plays major role in steel industry. It has been found that as compared to other countries, in India because of sponge iron sector the general percentage of lumps treatment in steel making (47%) is more than most other countries. As has been felt because of reducing hard iron ore, lump generation appropriate for blast furnace operation is getting down resulting in production of huge quantity of excess fines.

Other substitute of iron making processes for steel production may lead to shifting pattern of use raw material contributions and feed stock which may further lead to significant change in corresponding portion of lumps and agglomerated iron ore (sinter & pellets) and will also allow the use of ores which could not be exploited previously.

As fines constitutes significant amount of iron ore resources, value addition to their iron ore fines via several actions such as pelletisation, beneficiation is the real requirement.

INTRODUCTION

The iron ore mining called as Dalli-Rajhara Iron ore complex is the established iron ore mining belt in the eastern part of India in Chhattisgarh state. This includes Dalli Rajhara manual and mechanized mines, Jhara Dalli mines, Mahamaya mines. Rajhara mine was developed in the year 1960 and Dalli mine was developed in the year 1962. The ore processing plant of Rajhara involves 3- stage crushing and screening to produce BF grade lumps and sinter grade fines. The ore processing plant of Dalli involves 2-stage crushing, scalping and scrubbing, wet screening and finally classification.

The above mines are a part of Rajhara hill lease and Mahamaya- Dulki lease of Balod district, Chhattisgarh. The said deposits show characteristics of low to moderate

grade ore like Hematite as ore minerals and Quartz, as gangue minerals. Goethite covers around 10% area as a whole. All Goethite grains are in less than 30 micron size, out of which around 2% grains are in free-state and remaining 8% grains are not liberated. All un-liberated grains are in less than 20 micron size.

CHALLENGES

Post modernisation and expansion, the need of iron ore for BSP will be around 14 MTPA. Iron ore reserves of the said mines are depleting very fast and it is becoming difficult to meet the requirement of plant. Considering this aspect, BSP is the process of developing Rowghat mine to meet the future requirement of iron ore.

About 9.47 Mt of low grade fines generated in course of mining have been stored in the form of dumps. Fe content varies from 55% to 58%, and silica varies from 7.1 % to 9.5%. For fines to be utilised in steel plants, their quality has to meet the technological requirement of ore handling plants, sinter plants and blast furnaces in terms of size, desired lower alumina and silica content.

Wet circuit iron ore processing generates slimes to the tune of 10 to 15 % of run-off-mine (ROM). In Dalli mines, which is processing iron ore through wet circuit, 0.7 MT slimes are produced per annum. About 14.5 MT of slimes has accumulated in the Hitkasa tailing pond. Fe content varies from 49% to 55%.

As the mining gets in deeper benches high silica content is found in the ore .

Low grade fines and slime occupy huge space and cause environmental and ecological problems.

MANAGING IRON ORE FINES AND SLIMES

Beneficiation has a major role to play in utilisation of low grade ore/fines in iron making. It will help in conservation of mineral wealth and mitigation of adverse impact on environment. Combination of beneficiation, sintering and pelletisation of ore will result in increased use of fines in iron making.

Amenability to beneficiation has been established through laboratory scale and pilot scale tests. Beneficiation of Generated fines will be done by Jigging, Spiraling and Grinding mills.

Reclamation of slime from tailing pond will be done by excavators and tippers. The slime beneficiation circuit will consist of hydro-cyclones, magnetic separators, ball mills and concentrate thickeners. Since the products of slime beneficiation will be of very fine nature (<100micrometer), pelletisation has been considered as the next logical step. Pilot scale studies have been carried out successfully for production of BF grade pellets from the said beneficiated iron ore concentrate.

1. AGM, CET, Bhilai Sub Centre, 2.Sr.Mgr.(Mines-Project), BSP

Pelletisation process will include processes like grinding of raw material, balling and induration of green balls.

The final product will be

1. Sinter grade fines (-8mm size) having average Fe content 64%, Silica 3.5% and Alumina 1.65%
2. Pellets (9-16mm size) having average Fe content 65 %

Rejects of slime beneficiation plant will be disposed after pressure filtration in the form of solids (containing around 20% moisture) in a new tailing dump.

BENEFITS ENVISAGED

Beneficiation will help in conservation of mineral wealth. Low-grade ores, slimes and micro fines with iron content lower than 50% will be used, resulting in increase in mine life and reduction of waste.

Adverse environmental impact due to accumulated slime, dumped low grade fines shall be mitigated.

Phenomenal Environmental emissionsefficiency in agglomeration

Process	SO X, gm/t	NO X, gm/t	CO, kg/t	CO 2, kg/t	Particulate, gm/t
Sintering	1670	640	38	220	260
Pelletising, hematite ore	200	500	1	30	130
Pelletising, Magnetite ore	100	200	<1	25	125

Good Techno-economics:Charging of pellets in blast furnaces will improve the performance of the furnaces, which will be reflected in lower coke rate, higher productivity and improved hot metal quality as it is characterized by:

- (a)Good Reducibility:Because of their high porosity that is (25-30%), pellets are usually reducedconsiderably faster than hard burden sinter or hard natural ores/lump ores and high metallizationtakes place.
- (b)Good Bed Permeability:Their spherical shapes and containing open pores, gives them good bedpermeability.
- (c)In this the heat consumption is less.

CONCLUSION

Mineral resource need to be conserved and extracted optimally in an ecologically acceptable manner to ensure sustainable development.Since iron ore reserves are

[Type text]

depleting very fast, increasing the mineral resource base and full exploitation of available resource is the need of the hour.

REFERENCES

1. Mines, The Lifeline Of Bhilai—Yesterday, Today and tomorrow,Nov.2011,SAIL,Bhilai Steel Plant
2. Minetech"11: Mining technology for Sustainable Development ,Nov.2011
3. Feasibility Report, CET/01/RN/3520/FR/RM/01/R=5,April 2014,
4. SURESH KUMAR* & T.M. SRINIVASAN**